

RHEOFALT WKR-2

Product Data

Properties	Method	Specification
Congealing point	ASTM D 3104	102 - 108 °C
Penetration at 25 °C	ASTM D 1321	0 - 4 *0.1mm
Viscosity at 160 °C	ASTM D 3236	3200 - 4000 Mpa.s
Shape		pallets
Colour	visible	yellow / brown
Advised mixture with Bitumen 80-100	visual	15-20%

Effects of Bitumen

%-addition		0	18
Bitumen 80/100		100	0 - 4 *0.1mm
Congealing point *1		50°C	78°C
Penetration *2	25°C	76-80	26
	40°C	> 300	80
Viscosity	140°C	365 Mpa.s	1250 Mpa.s
	160°C	140 Mpa.s	450 Mpa.s
	180°C	70 Mpa.s	220 Mpa.s

We reserve the right to change the specifications as a result of technical progress or for reasons related to production. No guarantee or warranty is implied as to any particular applications of our products.